

# **DUNBAR – 1625W**

### 2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING

## **Applications**

DUNBAR-1625W is designed for general purpose applications such as the insulation and strain relief of electrical connections and terminations, light-duty harnessing, jacketing and bundling. The adhesive lining forms an environmental seal that helps protect against moisture.

#### **Features**

- ★ Shrink ratio: 50% or more in the radial direction, 5% or less in the axial direction
- ★ In stock for immediate shipments
- ★ Continuous operating temperature: 55 °C (-67 °F) to 110 °C (230 °F)
- ★ Flammability: UL VW-1 (Jacket only except clear)
- ★ Excellent electrical properties

#### **Standard**

- ★ AMS-DTL-23053/4 Class 2 (Formerly MIL-DTL-23053/4 Class 2)
- ★ UL 224 (File Number: E319314)
- **★** RoHS Compliant

# **Specification Values**

Property			Test Method	Value		
Physical	Unaged	Tensile strength	ASTM D638	Min. 1500 psi		
		Elongation	ASTIVI DOSO	Min. 200%		
	Fluid Resist.	Tensile strength	ASTM D638	Min. 1000 psi		
		Dielectric strength	ASTM D2671	Min. 400 Volts/mil		
	Heat shock		250 ℃/4 hrs	No cracks, flowing, or dripping		
	Low temperature flex		ASTM D746	No crack @-55°C		
	Secant Modulus		ASTM D882	Max. 25,000 psi		
	Heat Resistance		ASTM D2671	No cracks		
Electrical	Dielectric strength		ASTM D2671	Min. 500 Volts/mil		
	Volume resistivity		ASTM D876	Min. $1x10^{12}Ω$ - cm		
Chemical	Copper corrosion		121°C/16hrs	No corrosion		
	Fungus resistance		ASTM G21	No growth		
	Water Absorption		ASTM D570	Max. 0.5%		
	Flammak	oility	ASTM D2671	Pass		

Rev. Feb 2015




Tel: (469) 568-0800 Fax: (469) 568-0808



# **DUNBAR - 1625W**

2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING



## **Product Dimensions**

Minimum Shrink Temperature: 120 ℃

Size	Expanded		Recovered						
	Internal Diameter Minimum (D)		Internal Diameter Maximum (d)		Minimum Total Wall Thickness (Total Wall) (T)		Nominal Wall Thickness (Adhesive Wall) (t)		
Inch Size	ln.	mm	ln.	mm	ln.	mm	ln.	mm	
1/8"	0.138	3.51	0.062	1.57	0.017	0.43	0.004	0.102	
3/16"	0.197	5.01	0.093	2.36	0.017	0.43	0.004	0.102	
1/4"	0.238	6.06	0.125	3.18	0.024	0.61	0.004	0.102	
3/8"	0.355	9.02	0.187	4.75	0.024	0.61	0.004	0.102	
1/2"	0.475	12.07	0.250	6.35	0.025	0.64	0.005	0.127	
3/4"	0.712	18.08	0.375	9.53	0.030	0.76	0.005	0.127	
1"	0.950	24.13	0.500	12.70	0.035	0.89	0.007	0.178	
1-1/2"	1.425	36.20	0.750	19.05	0.039	0.99	0.007	0.178	

Rev. Feb 2015



Fax: (469) 568-0808