

FEP1.67

1.67:1 SHRINK RATIO, FLUORINATED ETHYLENE PROPYLENE TUBING

Applications

FEP1.6 is a flame retardant heat shrinkable fluorinated ethylene propylene tube. It has a high shrink ratio with a medium wall.

Features

- ★ In stock for immediate shipments
- ★ Shrink ratio: 1.67:1 shrink ratio in the radial direction, ± 15% in the axial direction
- ★ Continuous operating temperature: 75°C to 200°C
- ★ High resistance to chemicals and oils

Standard

- ★ MIL-DTL-23053/11 Class 2
- ★ RoHS Compliant

Specification Values

| Property | | Test Method | Value | |
|------------|--------------------------------|-------------|---------------------------------|--|
| Physical | Specific Gravity | ASTM D792 | 2.13-2.17 grams/cm ³ | |
| | Elongation | ASTM D638 | 250-330% | |
| | Tensile Strength | ASTM D638 | 2800-5000 psi | |
| | Flexural Strength | ASTM D790 | No break | |
| | Compressive Strength | ASTM D695 | 2000 psi | |
| | Flexural Modulus | ASTM D790 | 78000-92000 psi | |
| | Hardness Durometer | ASTM D636 | D-55 | |
| | Abrasion Resistance | Taber | 14-20 (1000 revs) | |
| Electrical | Dielectric Strength | ASTM D149 | 500 (125 MIL) | |
| | Dielectric Strength | ASTM D149 | ≥1400 (10 MIL) | |
| | Volume Resistivity | ASTM D257 | $>10^{18}\Omega$ - cm | |
| | Surface Resistivity | ASTM D257 | $>10^{17}\Omega$ - cm | |
| General | Chemical/Solvent Resistance | ASTM D543 | No corrosion | |
| | Water Absorption | ASTM D570 | <0.01 | |
| | Deformation Under Load | ASTM D621 | No growth | |
| | Flammability Rating | UL 94 | V -0 | |

Rev. Feb 2015




Fax: (469) 568-0808



FEP1.67

1.6:1 SHRINK RATIO, FLUORINATED ETHYLENE PROPYLENE TUBING



Fully recovered after heating

Product Dimensions Minimum Shrink Temperature: 210 °C (over 1" Dia. 221 °C)

| Product Dimensions Minimum Shrink Temperature: 210°C (over 1" Dia. 221°C) | | | | | | | | | |
|---------------------------------------------------------------------------|------------------------------------|-------|------------------------------------|-------|-----------------------------|-------------|----------|--|--|
| | Expanded | | Recovered | | | | | | |
| Size | Internal Diameter (min.) (D) | | Internal Diameter (max.) (d) | | Total Wall Thickness (t) | | 23053/11 | | |
| | ln. | mm | ln. | mm | In. | mm | Class 2 | | |
| 3/32" | .093 | 2.36 | .056 | 1.42 | .008 ± .003 | .203 ± .076 | 201 | | |
| 1/8" | .125 | 3.18 | .075 | 1.91 | .010 ± .003 | .254 ± .076 | 202 | | |
| 3/16" | .188 | 4.78 | .115 | 2.92 | .010 ± .003 | .254 ± .076 | 203 | | |
| 1/4" | .250 | 6.35 | .150 | 3.81 | .010 ± .003 | .254 ± .076 | 204 | | |
| 3/8" | .375 | 9.53 | .225 | 5.72 | .012 ± .003 | .305 ± .076 | 205 | | |
| 1/2" | .500 | 12.70 | .300 | 7.62 | .015 ± .004 | .381 ± .102 | 206 | | |
| 3/4" | .750 | 19.05 | .450 | 11.43 | .020 ± .004 | .508 ± .102 | 207 | | |
| 1" | 1.000 | 25.40 | .600 | 15.24 | .025 ± .005 | .635 ± .127 | 208 | | |
| 1-1/2" | 1.500 | 38.10 | .900 | 22.86 | .030 ± .005 | .762 ± .127 | 209 | | |
| 2" | 2.000 | 50.80 | 1.200 | 30.46 | .030 ± .005 | .762 ± .127 | 210 | | |

Rev. Feb 2015



Fax: (469) 568-0808