

## PTFE0S

# NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING STANDARD WALL (AWG Spaghetti sized tubing)

### **Applications**

PTFE0S is a non-shrink, flame retardant heat shrinkable polytetrafluoroethylene tube. It is designed for a wide range of applications requiring high heat-resistance.

#### **Features**

★ In stock for immediate shipments

★ Continuous operating temperature: - 75 °C to 260 °C

★ Flammability: UL VW-1★ Highly heat-resistant

★ High resistance to chemicals and oils

#### **Standard**

★ UL 224 (File Number: E103313)

★ MIL-DTL-22129-C ★ RoHS Compliant

## **Specification Values**

| Property   |                        | Test Method | Value                 |  |
|------------|------------------------|-------------|-----------------------|--|
| Physical   | Specific Gravity       | ASTM D792   | 2.13-2.0              |  |
|            | Elongation             | ASTM D638   | 200-450%              |  |
|            | Tensile Strength       | ASTM D638   | 2000-4500 psi         |  |
|            | Flexural Strength      | ASTM D790   | No break              |  |
|            | Compressive Strength   | ASTM D695   | 3500 psi              |  |
|            | Flexural Modulus       | ASTM D790   | 71000-85000 psi       |  |
|            | Hardness Durometer     | ASTM D636   | D-50-65               |  |
|            | Abrasion Resistance    | Taber       | 12 (1000 revs)        |  |
| Electrical | Dielectric Strength    | ASTM D149   | 500 (125 MIL)         |  |
|            |                        | ASTM D149   | ≥1400 (10 MIL)        |  |
|            | Volume Resistivity     | ASTM D257   | $>10^{18}\Omega$ - cm |  |
|            | Surface Resistivity    | ASTM D257   | $>10^{17}\Omega$ - cm |  |
| General    | Chemical/Solvent       | ASTM D543   | No corrosion          |  |
|            | Resistance             |             |                       |  |
|            | Water Absorption       | ASTM D570   | <0.01                 |  |
|            | Deformation Under Load | ASTM D621   | No growth             |  |
|            | Flammability Rating    | UL 94       | VO                    |  |

Rev. Feb 2015




Fax: (469) 568-0808



# PTFE0S

# NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING STANDARD WALL (AWG Spaghetti sized tubing)



#### **Product Dimensions**

| AWG<br>Size | Inside Diameter                  |      |                                |      |                             |             |  |
|-------------|----------------------------------|------|--------------------------------|------|-----------------------------|-------------|--|
|             | Internal Diameter<br>Inch<br>(D) |      | Internal Diameter<br>MM<br>(D) |      | Total Wall Thickness<br>(t) |             |  |
|             | Min                              | Max  | Min                            | Max  | In                          | mm          |  |
| 30          | .010                             | .015 | .25                            | .38  | .009 ± .002                 | .229 ± .051 |  |
| 28          | .013                             | .018 | .33                            | .48  | .009 ± .002                 | .229 ± .051 |  |
| 26          | .016                             | .021 | .41                            | .53  | .009 ± .002                 | .229 ± .051 |  |
| 24          | .020                             | .026 | .51                            | .66  | .012 ± .002                 | .304 ± .051 |  |
| 23          | .023                             | .029 | .58                            | .74  | .012 ± .002                 | .304 ± .051 |  |
| 22          | .026                             | .032 | .66                            | .81  | .012 ± .002                 | .304 ± .051 |  |
| 21          | .029                             | .035 | .74                            | .89  | .012 ± .002                 | .304 ± .051 |  |
| 20          | .032                             | .040 | .81                            | .97  | .016 ± .003                 | .406 ± .076 |  |
| 19          | .036                             | .042 | .91                            | 1.06 | .016 ± .003                 | .406 ± .076 |  |
| 18          | .040                             | .046 | 1.02                           | 1.17 | .016 ± .003                 | .406 ± .076 |  |
| 17          | .045                             | .052 | 1.14                           | 1.32 | .016 ± .003                 | .406 ± .076 |  |
| 16          | .051                             | .058 | 1.30                           | 1.47 | .016 ± .003                 | .406 ± .076 |  |
| 15          | .057                             | .065 | 1.45                           | 1.65 | .016 ± .003                 | .406 ± .076 |  |
| 14          | .064                             | .072 | 1.63                           | 1.83 | .016 ± .003                 | .406 ± .076 |  |
| 13          | .072                             | .081 | 1.83                           | 2.06 | .016 ± .003                 | .406 ± .076 |  |
| 12          | .081                             | .091 | 2.08                           | 2.31 | .016 ± .003                 | .406 ± .076 |  |
| 11          | .091                             | .101 | 2.31                           | 2.57 | .016 ± .003                 | .406 ± .076 |  |
| 10          | .102                             | .112 | 2.59                           | 2.84 | .016 ± .003                 | .406 ± .076 |  |
| 9           | .114                             | .124 | 2.90                           | 3.15 | $.020 \pm .004$             | .508 ± .102 |  |
| 8           | .129                             | .139 | 3.28                           | 3.53 | $.020 \pm .004$             | .508 ± .102 |  |
| 7           | .144                             | .155 | 3.68                           | 3.94 | .020 ± .004                 | .508 ± .102 |  |
| 6           | .162                             | .174 | 4.11                           | 4.42 | .020 ± .004                 | .508 ± .102 |  |
| 5           | .182                             | .195 | 4.62                           | 4.95 | .020 ± .004                 | .508 ± .102 |  |
| 4           | .204                             | .218 | 5.18                           | 5.54 | .020 ± .004                 | .508 ± .102 |  |
| 3           | .229                             | .244 | 5.82                           | 6.19 | .020 ± .004                 | .508 ± .102 |  |
| 2           | .258                             | .273 | 6.55                           | 6.93 | .020 ± .004                 | .508 ± .102 |  |
| 1           | .289                             | .305 | 7.34                           | 7.75 | .020 ± .004                 | .508 ± .102 |  |
| 0           | .325                             | .342 | 8.26                           | 8.69 | .020 ± .004                 | .508 ± .102 |  |

Rev. Feb 2015



Tel: (469) 568-0800 Fax: (469) 568-0808